

12

EUROPEAN PATENT APPLICATION

21 Application number: 89307851.9

51 Int. Cl.⁵: **C 11 D 3/00**
C 11 D 3/37

22 Date of filing: 02.08.89

30 Priority: 04.08.88 US 228079

43 Date of publication of application:
07.02.90 Bulletin 90/06

84 Designated Contracting States:
BE DE ES FR GB NL

71 Applicant: **DOW CORNING CORPORATION**
3901 S. Saginaw Road
Midland Michigan 48686-0994 (US)

72 Inventor: **Starch, Michael Stephen**
2644 N. 5 Mile Road
Midland Michigan (US)

74 Representative: **Lewin, John Harvey et al**
ELKINGTON AND FIFE Beacon House 113 Kingsway
London WC2B 6PP (GB)

54 **Dispersible silicone antifoam formulations.**

57 A dispersible silicone antifoam composition for providing controlled foaming liquid laundry detergent formulations and wherein there is provided a non-aqueous emulsion of primary and secondary silicone antifoam agents, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent.

EP 0 354 016 A2

Description

DISPERSIBLE SILICONE ANTIFOAM FORMULATIONS

This invention relates to a dispersible silicone antifoam composition for providing controlled foaming liquid laundry detergent formulations and wherein there is provided a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a mixture of (a) a polyorganosiloxane fluid having at least one hydroxyl and/or hydrocarboxy group, (b) a resinous siloxane or a silicone resin-producing silicon compound, (c) a finely divided filler material, and (d) a catalyst to promote the reaction of (a) to (c), the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent.

The invention also relates to a dispersible silicone antifoam composition for providing controlled foaming aqueous medium formulations and wherein there is provided a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a mixture of (a) a polyorganosiloxane fluid having at least one hydroxyl and/or hydrocarboxy group, (b) a resinous siloxane or a silicone resin-producing silicon compound, (c) a finely divided filler material, and (d) a catalyst to promote the reaction of (a) to (c), the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the aqueous medium and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the aqueous medium.

In another embodiment of the present invention, the primary antifoam agent may also include a polyorganosiloxane fluid which is substantially free of reactive groups. The nonionic silicone surfactant is a material including trimethylsilyl endcapped polysilicate which has been condensed with a polyalkylene glycol or diester in a solvent. Optionally, another silicone surfactant can be included such as a copolymer of polymethylsiloxane and polyalkylene oxide in a solvent. In a specific embodiment, the secondary antifoam agent has a viscosity of about one thousand centistokes, the solvent is polypropylene glycol having an average molecular weight of about two thousand and the block copolymer is an ethylene oxide-propylene oxide block copolymer.

The most preferred primary antifoam agent is that formulation of U.S. Patent Nos. 4,639,489 and

4,749,740, which formulation covers a silicone defoamer composition produced by reacting at a temperature of 50°C. to 300°C.:

(1) 0 to 100 parts by weight of a polyorganosiloxane having a viscosity of 20 to 100,000 cs at 25°C. and being expressed by the general formula $R^1_nSiO_{(4-n)/2}$ in which R^1 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms and has an average value of from 1.9 to 2.2;

(2) less than five parts by weight of a polyorganosiloxane having a viscosity of 200 to several million cs at 25°C. expressed by the general formula $R^2_b(R^3O)_cSiO_{(4-b-c)/2}$ in which R^2 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R^3 is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, b has an average value of from 1.9 to 2.2 and c has a sufficiently large value to give at least one $-OR^3$ group in each molecule, said $-OR^3$ group being present at least at the end of a molecular chain; the total of components (1) and (2) being 100 parts by weight;

(3) 0.5 to 20 parts by weight for every 100 parts by weight of said components (1) and (2) of one or more compounds selected from the following a) to d):

a) an organosilicon compound of the general formula $R^4_dSiX_{4-d}$ in which R^4 is a monovalent hydrocarbon group having 1 to 5 carbon atoms, X is a hydrolyzable group and d has an average value of one or less;

b) a partially hydrolyzed condensate of said compound a);

c) a siloxane resin consisting essentially of $(CH_3)_3SiO_{1/2}$ and SiO_2 units and having a $(CH_3)_3SiO_{1/2}/SiO_2$ ratio of 0.4/1 to 1.2/1; and

d) a condensate of said compound c) with said compound a) or b);

(4) 0.5 to 30 parts by weight of a finely divided filler for every 100 parts by weight of said components (1) and (2);

(5) a catalytic amount of a compound for promoting the reaction of the other components; and

(6) 0 to 20 parts by weight, for every 100 parts by weight of said components (1) and (2), of a polyorganosiloxane having a viscosity of 5 to 200 cs at 25°C. and being expressed by the general formula $R^8_e(R^9O)_fSiO_{(4-e-f)/2}$ in which R^8 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R^9 is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, e is from 1.9 to 2.2 on an average and f has a sufficiently large value to give at least two $-OR^9$ groups in each molecule at the end of a molecular chain.

In this formulation, the R¹ groups of component (1), the R² groups of component (2) and the R⁸ groups of component (6) are hydrocarbon groups; the X groups of component (3) a) are -OR⁵ groups or -OR⁶OR⁷ groups in which R⁶ is a divalent hydrocarbon group having 1 to 5 carbon atoms and R⁵ and R⁷ are each hydrogen or a monovalent hydrocarbon group having 1 to 5 carbon atoms; component (4) is silica; and component (5) is a compound selected from the group consisting of alkali metal hydroxides, alkali metal silanates, alkali metal alkoxides and metal salts of organic acids. Further, component (1) is a trimethylsiloxy-end-blocked polydimethylsiloxane fluid having a viscosity of from 350 to 15,000 centistokes at 25°C.; component (2) is a hydroxyl-endblocked polydimethylsiloxane fluid having a viscosity of from 1,000 to 50,000 centistokes of 25°C.; component (4) is a silica having a surface area of from 50 to 500 m²/g; and component (6) is a hydroxyl-endblocked polydimethylsiloxane having a viscosity of from 10 to 50 centistokes at 25°C.

It is, therefore, an object of the present invention to provide an easily dispersible silicone antifoam composition for use in a liquid laundry detergent and wherein there is provided controlled foaming behavior.

It is another object of the present invention to provide a homogeneously dispersible silicone antifoam formulation for a liquid laundry detergent or an aqueous medium and wherein the antifoam composition can be dispersed into the liquid laundry detergent or the aqueous medium in order to form stable, relatively clear formulations having controlled foaming behavior.

These and other features, objects and advantages, of the herein described present invention will become apparent when taken in conjunction with the following detailed description.

The single figure of drawing is a functional representation of automated pump testing apparatus used to determine the performance of antifoam compositions under conditions designed to simulate consumer use.

In accordance with the present invention, an antifoam formulation is provided wherein an antifoam is rendered dispersible in aqueous mediums, especially liquid laundry detergents, by means of a plurality of particular surfactant and dispersing agents which function as emulsifying ingredients. Preferred emulsifying and dispersing ingredients for the purposes of the present invention are the nonionic or anionic surfactant type. In nonionic surfactants, for example, there is no charge on the molecule and the solubilizing groups are ethylene oxide chains and hydroxyl groups. Such nonionic surfactants are compatible with ionic and amphoteric surfactants and representative of nonionic surfactants are, for example, polyoxyethylene or ethoxylate surfactants such as alcohol ethoxylates and alkylphenol ethoxylates. Carboxylic acid ester nonionic surfactants include glycerol esters, polyoxyethylene esters, anhydrosorbitol esters, ethoxylated anhydrosorbitol esters, natural fats, oils and waxes and ethoxylated and glycol esters of fatty

acids. Carboxylic amide nonionic surfactants which may be included are diethanolamine condensates, monoalkanolamine condensates and polyoxyethylene fatty acid amide. Representative of polyalkylene oxide block copolymer nonionic surfactants are the polyalkylene oxides derived from ethylene, propylene, butylene, styrene and cyclohexene. Typical of the anionic surfactants that may be employed herein are salts of alkyl sulfates, salts of alkylaryl sulfates, salts of alkyl ether sulfates, salts of alkylaryl ether sulfates and salts of alkylaryl sulfonates. Exemplary materials included are, for example, alkyl benzene sulfonates, alkyl glyceryl ether sulfonates, alkyl phenol ethylene oxide ether sulfates, esters of alpha-sulfonated fatty acids, 2-acyloxyalkane-1-sulfonic acids, olefin sulfonates, beta-alkyloxyalkane sulfonates, anionic surfactants based on higher fatty acids and tallow range alkyl sulfates. Both categories of surfactant are well known in the art and are described in more or less detail in U.S. Patent No. 4,075,118, issued February 21, 1978, for example.

Because, as noted hereinbefore, antifoams are difficultly dispersible in aqueous mediums such as liquid laundry detergent formulations, the particular combination of surfactants and dispersants used herein is important in accordance with the present invention in that such surfactant-dispersant combinations serve to render antifoams easily dispersible, emulsifiable and homogeneous in aqueous medium applications. According to the present invention, the preferred silicone antifoam formulation which forms the basis of the primary antifoam agent used herein, is the defoamer composition disclosed and described in U.S. Patent No. 4,639,489, issued January 27, 1987 and U.S. Patent No. 4,749,740 issued June 7, 1988 and which defoamer composition is a multi-component system. The defoamer composition of U.S. Patent No. 4,639,489 and 4,749,740, includes as multi-components a mixture of (a) a polyorganosiloxane fluid having at least one hydroxyl and/or hydrocarbonoxy group, (b) a polyorganosiloxane fluid which is substantially free of reactive groups, (c) a resinous siloxane or a silicone resin-producing silicon compound, (d) a finely divided filler material, and (e) a catalyst to promote the reaction of (a) to (d). The specifics and details of each of the various components of this primary antifoam composition are set forth in the aforementioned U.S. Patents No. 4,639,489 and No. 4,749,740.

The antifoam composition of the present invention also preferably includes a secondary antifoam agent for use in conjunction with the primary antifoam agent and the secondary antifoam agent is described hereinafter.

In order to render the primary and secondary antifoam agents dispersible in aqueous medium, more particularly liquid laundry detergent formulations, there is included along with the two antifoam agents, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent; an organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent and a dispersing agent of a

nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent. One nonionic silicone surfactant can be a copolymer of polymethylsiloxane and polyalkylene oxide in a solvent or a material including trimethylsilyl end-capped polysilicate which has been condensed with a polyalkylene glycol or diester in a solvent. The term solvent as used herein is intended to include polypropylene glycol having an average molecular weight of about two thousand. The block copolymer preferred is an ethylene oxide-propylene oxide block copolymer. The nonionic organic surfactant employed is TRITON® X-100, a material of the formula $C_8H_{17}C_6H_4(OCH_2CH_2)_9OH$, manufactured by Rohm and Haas, Philadelphia, Pennsylvania. TRITON® is a registered trademark of Rohm and Haas. The block-copolymer employed is PLURONIC® L-101, a product of BASF-Wyandotte Corporation, Parsippany, New Jersey. PLURONIC® is a registered trademark of BASF-Wyandotte. PLURONIC® L-101 is a difunctional block-copolymer terminating in primary hydroxyl groups and with a molecular weight that may range from about one to about fifteen thousand. PLURONIC® L-101 is a polyalkylene oxide derivative of propylene glycol.

While the compositions of the present invention can be used in conjunction with many formulations of detergents, by way of example, the liquid laundry detergent compositions set forth in U.S. Patent Nos. 4,318,818, issued March 9, 1982; 4,507,219, issued March 26, 1985; 4,515,705, issued May 7, 1985; and 4,597,898, issued July 1, 1986; are most exemplary. The antifoam formulations of the present invention can be mixed directly into such liquid laundry detergents to provide an essentially clear detergent with reduced foaming behavior. Preferably, the primary and the secondary antifoam agents are mixed and emulsified in polypropylene glycol of average molecular weight of about two thousand, with the two nonionic silicone surfactants, followed by addition of the organic nonionic surfactant and the block-copolymer, and then the formulation is mixed with the aqueous medium, or in the preferred embodiment, a liquid laundry detergent of the type noted above. The various components of the formulation of the present invention, other than the particular antifoam components of U.S. Patent No. 4,639,489 and 4,749,740, function as the delivery mechanism for the antifoam composition of U.S. Patent No. 4,639,489 and 4,749,740, in order to permit dispersion of the antifoam of U.S. Patent No. 4,639,489 and 4,749,740, in aqueous mediums.

The polydimethylsiloxane used herein as the secondary antifoam agent is a high molecular weight polymer having a molecular weight in the range from about 200 to about 200,000 and have a viscosity in the range from about 20 to 2,000,000 centistokes, preferably from about 500 to 50,000 centistokes, more preferably about 1,000 centistokes at 25°C. The siloxane polymer is generally end-blocked either with trimethylsilyl or hydroxyl groups but other end-blocking groups are also suitable. The polymer can be prepared by various techniques such as the

hydrolysis and subsequent condensation of dimethyldihalosilanes or by the cracking and subsequent condensation of dimethylcyclorosiloxanes.

The polydimethylsiloxane secondary antifoam agent can be present in combination with particulate silica. Such combinations of silicone and silica can be prepared by affixing the silicone to the surface of silica for example by means of the catalytic reaction disclosed in U.S. Patent No. 3,235,509. Foam regulating agents comprising mixtures of silicone and silica prepared in this manner preferably comprise silicone and silica in a silicone: silica ratio of from 20:1 to 200:1, preferably about 25:1 to about 100:1. The silica can be chemically and/or physically bound to the silicone in an amount which is preferably about 0.5% to 5% by weight, based on the silicone. The particle size of the silica employed in such silica/silicone foam regulating agents is finely divided and should preferably be not more than 100 millimicrons preferably from 10 millimicrons to 20 millimicrons and the specific surface area of the silica should exceed about 50 m²/g.

Alternatively, silicone and silica can be prepared for use as the secondary antifoam agent by admixing a silicone fluid of the type herein disclosed with a hydrophobic silica having a particle size and surface area in the range disclosed above. Any of several known methods may be used for making a hydrophobic silica which can be employed herein in combination with a silicone as the secondary foam regulating agent. For example, a fumed silica can be reacted with a trialkyl chlorosilane (i.e., "silanated") to affix hydrophobic trialkylsilane groups on the surface of the silica. In a preferred and well known process, fumed silica is contacted with trimethylchlorosilane. A preferred material comprises a hydrophobic silanated (most preferably trimethylsilanated) silica having a particle size in the range from about 10 millimicrons to 20 millimicrons and a specific surface area above about 50 m²/g intimately admixed with a dimethylsilicone fluid having a molecular weight in the range of from about 500 to about 200,000, at a weight ratio of silicone to silanated silica of from about 20:1 to about 200:1, preferably from about 20:1 to about 100:1.

Yet another type of material suitable herein as the secondary antifoam comprises polydimethylsiloxane fluid, a silicone resin and silica. The silicone "resins" used in such compositions can be any alkylated silicone resins, but are usually those prepared from methylsilanes. Silicone resins are commonly described as "three-dimensional" polymers arising from the hydrolysis of alkyl trichlorosilanes, whereas the silicone fluids are "two-dimensional" polymers prepared from the hydrolysis of dichlorosilanes. The silica components of such compositions are microporous materials such as fumed silica aerogels and xerogels having particle sizes and surface areas herein-above disclosed.

The mixed polydimethylsiloxane fluid/silicone resin/silica materials useful in the present compositions as secondary antifoam agents can be prepared in the manner disclosed in U.S. Patent No. 3,455,839. Preferred materials of this type comprise:

(a) from about 10 parts to about 100 parts by

weight of a polydimethylsiloxane fluid having a viscosity in the range from 20 to 30,000 mm/s at 25°C.;

(b) 5 to 50 parts by weight of a siloxane resin composed of $(\text{CH}_3)_3\text{SiO}_{1/2}$ units and SiO_2 units in which the ratio of the $(\text{CH}_3)_3\text{SiO}_{1/2}$ units to the SiO_2 units is within the range of from 0.6/1 to 1.2/1; and

(c) 0.5 to 5 parts by weight of a silica aerogel. Such mixtures can also be sorbed onto and into a water-soluble solid.

Antifoam compositions prepared in accordance with the present invention were prepared and tested in order to demonstrate their defoaming capabilities and to determine the effectiveness of the antifoam compositions.

Testing of the invention was carried out to determine the performance under conditions designed to simulate consumer use. The apparatus used was an automated pump tester. The pump tester apparatus is shown in the drawing and consists of a large 15 gallon cylindrical plastic vessel for holding a quantity of simulated wash liquor or laundry detergent in water and two pumps which circulate the wash liquor. Plastic hoses are arranged so that the wash liquor is drawn from the vessel by the first pump and passed through a valve where a controlled amount of air is introduced into the liquid. A second pump mixes the air and wash liquor and returns the mixture to the vessel. When the pumps are started, a column of foam collects on the surface of the liquid in the vessel. The height of this foam column is detected by an ultrasonic ranging device which is connected to a computer so that foam height measurements are recorded at regular time intervals. Thus the apparatus is used to generate a series of foam height versus time plots which are used to determine the performance of foam control agents.

The wash liquor is prepared by dispersing a measured amount of a commercial liquid laundry detergent in 8.6 liters of deionized water to which has been added a known amount of calcium chloride solution. The purpose of the calcium chloride is to simulate water hardness, which is known to have an effect on the foaming properties of laundry detergents. The amount of liquid laundry detergent added to the simulated hard water is calculated by taking the detergent manufacturer's recommended amount for a washing machine and reducing it by a factor to account for the difference in volume between a typical washing machine and the 8.6 liter volume used in the pump tester. For every evaluation, the foaming behavior of a particular liquid laundry detergent was compared to the same detergent to which the foam control composition has been added. Results of these tests are indicated below.

Example I

DASH® liquid laundry detergent manufactured by The Procter & Gamble Company, Cincinnati, Ohio, was selected as the control. This type of detergent typically includes surfactants such as linear aryl sulfonates, alkyl ether sulfates and alkyl ethoxylates;

a foam control agent of coconut fatty acid soap; builder-buffers such as sodium citrate, sodium tripolyphosphate and organic amines; hydrotropes such as propylene glycol, ethanol and sodium xylene sulfonate; and other ingredients such as enzymes, enzyme stabilizers, optical brighteners, perfumes, and dyes; and is described in more or less detail in the above mentioned U.S. Patent Nos. 4,318,818, 4,507,219, 4,515,705 and 4,597,898. Seventeen and one-half grams of clear DASH® liquid laundry detergent was added to the pump tester apparatus shown in the drawing, containing 8.6 liters of deionized water to which had been added calcium chloride to provide a concentration of calcium ions equivalent to sixty parts per million. The temperature of the water in the tank was sixty degrees Fahrenheit. The simulated wash liquor was recirculated through the pumps, air bleed valve and tank, and the foam height monitored by the ultrasonic sensor and recorded every forty seconds. The recirculation was continued for six hundred seconds and the average recorded foam height of the DASH® liquid laundry detergent was found to be 23.3 centimeters at the end of ten minutes.

Example II

Example I was repeated except that to the liquid laundry detergent, there was added one-tenth of one percent by weight of the dispersible antifoam composition of the present invention. The composition was formulated by first preparing a master batch of two hundred grams of antifoam composition. The antifoam composition included in parts by weight, twenty parts of the primary antifoam agent, being that composition set forth in U.S. Patent Nos. 4,639,489 and 4,749,740; ten parts of polydimethylsiloxane secondary antifoam agent of a viscosity of about one thousand centistokes; four and one-half parts of nonionic silicone surfactant of trimethylsilyl endcapped polysilicate; one and one-half parts of TRITON® X-100 being a nonionic organic surfactant; ten parts of PLURONIC® L-101 being another nonionic organic surfactant; and fifty-four parts of polypropylene glycol of an average molecular weight of about two-thousand. The pump test of Example I was repeated including DASH® liquid laundry detergent to which had been added one-tenth of one percent by weight of the foregoing antifoam composition. The simulated wash liquor including the DASH® liquid laundry detergent and the antifoam composition of the present invention was recirculated through the pumps, air bleed valve and tank and the foam height monitored by the ultrasonic sensor and recorded every forty seconds. The recirculation was continued for six hundred seconds and the average recorded foam height of the DASH® liquid laundry detergent containing the antifoam composition of the present invention was found to be 13.5 centimeters at the end of ten minutes, a reduction in foam height of almost ten centimeters as compared to the DASH® liquid laundry detergent of Example I which did not contain the antifoam composition of the present invention.

Example III

Example II was repeated except that instead of TRITON® X-100, there was substituted one part of TRITON® X-405 a nonionic organic surfactant and an octylphenoxy polyethoxy ethanol composition and one-half of one part of TRITON® W-30 an anionic organic surfactant and the sodium salt of an alkylaryl polyether sulfate. The PLURONIC® L-101 was also used in an amount of five parts instead of ten parts and the amount of polypropylene glycol was increased from fifty-four parts to fifty-nine parts. The pump test of Example II was repeated including DASH® liquid laundry detergent to which had been added one-tenth of one percent by weight of the foregoing modified antifoam composition. The simulated wash liquor including the DASH® liquid laundry detergent and the modified antifoam composition of the present invention was recirculated through the pumps, air bleed valve and tank and the foam height monitored by the ultrasonic sensor and recorded every forty seconds. The recirculation was continued for six hundred seconds and the average recorded foam height of the DASH® liquid laundry detergent containing the modified antifoam composition of the present invention was found to be 14.6 centimeters at the end of ten minutes, a reduction in foam height of almost nine centimeters as compared to the DASH® liquid laundry detergent of Example I which did not contain the antifoam composition of the present invention. Both the compositions of Examples II and III when mixed with the clear yellow colored liquid laundry detergent were found to result in yellowish solutions of relative clarity.

Example IV

Example 1 was repeated except that in addition to the DASH® liquid laundry detergent, there was included in the wash liquor one-tenth of one percent by weight of detergent of antifoam composition comparable to that described in Example No. 1 of the Keil U.S. Patent No. 3,784,479. The simulated wash liquor was recirculated through the pumps, air bleed valve and tank and the foam height monitored by the ultrasonic sensor and recorded every forty seconds. The recirculation was continued for six hundred seconds and the average recorded foam height of the DASH® liquid laundry detergent containing the Keil antifoam formulation was found to be about 20.9 centimeters at the end of ten minutes, indicating that the formulation in Keil is not as effective as an antifoam agent in liquid laundry detergents as are the formulations of the present invention and furthermore forms relatively hazy mixtures.

Whereas the particulate material of the secondary antifoam agent of the present invention has been illustrated by means of silica, it should be understood that other equivalent particulate materials may be used in accordance with the present invention. Thus, for example, there can be used in place of or in addition to silica, high surface area particulates such as crushed quartz, zirconium silicate, aluminum silicate, mica, ground glass and sand. The term "silica" as used herein is intended to include, for example, silica such as fume silica, precipitated

silica and treated silica such as fume silica and precipitated silica that has been reacted with an organohalosilane, a disiloxane or disilazane.

It will be apparent from the foregoing that many other variations and modifications may be made in the structures, compounds, compositions and methods described herein without departing substantially from the essential features and concepts of the present invention. Accordingly, it should be clearly understood that the forms of the invention described herein are exemplary only and are not intended as limitations on the scope of the present invention.

Claims

1. In a liquid laundry detergent containing surfactants, builders and at least one foam control agent, the improvement comprising a dispersible silicone antifoam composition for providing controlled foaming of the liquid laundry detergent comprised of a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a mixture of (a) a polyorganosiloxane selected from the group consisting of fluids having at least one hydroxyl and hydrocarbonoxy group, (b) a resinous siloxane or a silicone resin-producing silicon compound, (c) a finely divided filler material and (d) a catalyst to promote the reaction of (a) to (c), the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant, a first organic surfactant dispersing agent and a second dispersing agent of a nonionic difunctional block copolymer terminating in primary hydroxyl groups.

2. A dispersible silicone antifoam composition for providing controlled foaming aqueous medium formulations comprising a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a mixture of (a) a polyorganosiloxane selected from the group consisting of fluids having at least one hydroxyl and hydrocarbonoxy group, (b) a resinous siloxane or a silicone resin-producing silicon compound, (c) a finely divided filler material, and (d) a catalyst to promote the reaction of (a) to (c), the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant, a first organic surfactant dispersing agent and a second dispersing agent of a nonionic difunctional block copolymer terminating in primary hydroxyl groups.

3. A dispersible silicone antifoam composition for providing controlled foaming aqueous medium formulations comprising a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a mixture of (a) a polyorganosiloxane selected from the group consisting of fluids having at least one hydroxyl and hydrocarbonoxy group, (b) a polyorganosiloxane fluid

which is substantially free of reactive groups, (c) a resinous siloxane or a silicone resin-producing silicon compound, (d) a finely divided filler material, and (e) a catalyst to promote the reaction of (a) to (d), the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the aqueous medium and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the aqueous medium.

4. A dispersible silicone antifoam composition for providing controlled foaming liquid laundry detergent formulations comprising a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a silicone defoamer composition formed by reacting at a temperature of 50°C. to 300°C.: (1) 1 to 100 parts by weight of a polyorganosiloxane having a viscosity of 20 to 100,000 cs at 25°C. and being expressed by the general formula $R^1_aSiO_{(4-a)/2}$ in which R^1 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms and a has an average value of from 1.9 to 2.2;

(2) less than five parts by weight of a polyorganosiloxane having a viscosity of 200 to several million cs at 25°C. expressed by the general formula $R^2_b(R^3O)_cSiO_{(4-b-c)/2}$ in which R^2 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R^3 is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, b has an average value of from 1.9 to 2.2 and c has a sufficiently large value to give at least one -OR³ group in each molecule, said -OR³ group being present at least at the end of a molecular chain; the total of components (1) and (2) being 100 parts by weight;

(3) 0.5 to 20 parts by weight for every 100 parts by weight of said components (1) and (2) of one or more compounds selected from the following a) to d):

a) an organosilicon compound of the general formula $R^4_dSiX_{4-d}$ in which R^4 is a monovalent hydrocarbon group having 1 to 5 carbon atoms, X is a hydrolyzable group and d has an average value of one or less;

b) a partially hydrolyzed condensate of said compound a);

c) a siloxane resin consisting essentially of $(CH_3)_3SiO_{1/2}$ and SiO_2 units and having a $(CH_3)_3SiO_{1/2}/SiO_2$ ratio of 0.4/1 to 1.2/1; and d) a condensate of said compound c) with said compound a) or b);

(4) 0.5 to 30 parts by weight of a finely divided filler for every 100 parts by weight of said components (1) and (2);

(5) a catalytic amount of a compound for

promoting the reaction of the other components; and

(6) 1 to 20 parts by weight, for every 100 parts by weight of said components (1) and (2), of a polyorganosiloxane having a viscosity of 5 to 200 cs at 25°C. and being expressed by the general formula $R^8_e(R^9O)_fSiO_{(4-e-f)/2}$ in which R^8 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R^9 is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, e is from 1.9 to 2.2 on an average and f has a sufficiently large value to give at least two -OR⁹ groups in each molecule at the end of a molecular chain,

the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant, a first organic surfactant dispersing agent and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups.

5. A method of controlling the production of foam produced by a liquid laundry detergent in a wash liquor comprising adding to the detergent prior to the incorporation of the detergent into the wash liquor a dispersible silicone antifoam composition for providing a controlled foaming liquid laundry detergent comprised of a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a silicone defoamer composition formed by reacting at a temperature of 50°C. to 300°C.: (1) 1 to 100 parts by weight of a polyorganosiloxane having a viscosity of 20 to 100,000 cs at 25°C. and being expressed by the general formula $R^1_aSiO_{(4-a)/2}$ in which R^1 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms and a has an average value of from 1.9 to 2.2;

(2) less than five parts by weight of a polyorganosiloxane having a viscosity of 200 to several million cs at 25°C. expressed by the general formula $R^2_b(R^3O)_cSiO_{(4-b-c)/2}$ in which R^2 is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R^3 is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, b has an average value of from 1.9 to 2.2 and c has a sufficiently large value to give at least one -OR³ group in each molecule, said -OR³ group being present at least at the end of a molecular chain; the total of components (1) and (2) being 100 parts by weight;

(3) 0.5 to 20 parts by weight for every 100 parts by weight of said components (1) and (2) of one or more compounds selected from the following a) to d):

a) an organosilicon compound of the general formula $R^4_dSiX_{4-d}$ in which R^4 is a monovalent hydrocarbon group having 1 to 5 carbon atoms, X is a hydrolyzable group and d has an average value of one or less;

b) a partially hydrolyzed condensate of said compound a);

c) a siloxane resin consisting essentially of

(CH₃)₃SiO_{1/2} and SiO₂ units and having a (CH₃)₃SiO_{1/2}/SiO₂ ratio of 0.4/1 to 1.2/1; and
d) a condensate of said compound c) with said compound a) or b);

(4) 0.5 to 30 parts by weight of a finely divided filler for every 100 parts by weight of said components (1) and (2);

(5) a catalytic amount of a compound for promoting the reaction of the other components; and

(6) 1 to 20 parts by weight, for every 100 parts by weight of said components (1) and (2), of a polyorganosiloxane having a viscosity of 5 to 200 cs at 25°C. and being expressed by the general formula R⁸_e(R⁹O)_fSiO_{(4-e-f)/2} in which R⁸ is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R⁹ is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, e is from 1.9 to 2.2 on an average and f has a sufficiently large value to give at least two -OR⁹ groups in each molecule at the end of a molecular chain,

the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent.

6. A dispersible silicone antifoam composition for providing controlled foaming liquid laundry detergent formulations comprising a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a silicone defoamer composition formed by reacting at a temperature of 50°C. to 300°C.:

(1) less than five parts by weight of a polyorganosiloxane having a viscosity of 200 to several million cs at 25°C. expressed by the general formula R²_b(R³O)_cSiO_{(4-b-c)/2} in which R² is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R³ is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, b has an average value of from 1.9 to 2.2 and c has a sufficiently large value to give at least one -OR³ group in each molecule, said -OR³ group being present at least at the end of a molecular chain;
(2) 0.5 to 20 parts by weight for every 100 parts by weight of component (1) of one or more compounds selected from the following a) to d):

a) an organosilicon compound of the general formula R⁴_dSiX_{4-d} in which R⁴ is a monovalent hydrocarbon group having 1 to 5 carbon atoms, X is a hydrolyzable group and d has an average value of one or less;

b) a partially hydrolyzed condensate of said

compound a);

c) a siloxane resin consisting essentially of (CH₃)₃SiO_{1/2} and SiO₂ units and having a (CH₃)₃SiO_{1/2}/SiO₂ ratio of 0.4/1 to 1.2/1; and

d) a condensate of said compound c) with said compound a) or b);

(3) 0.5 to 30 parts by weight of a finely divided filler for every 100 parts by weight of component (1);

(4) a catalytic amount of a compound for promoting the reaction of the other components; and

the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic silicone surfactant, a first organic surfactant dispersing agent and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups.

7. A method of controlling the production of foam produced by a liquid laundry detergent in a wash liquor comprising adding to the detergent prior to the incorporation of the detergent into the wash liquor a dispersible silicone antifoam composition for providing a controlled foaming liquid laundry detergent comprised of a non-aqueous emulsion of primary and secondary antifoam agents, the primary antifoam agent being a silicone defoamer composition formed by reacting at a temperature of 50°C. to 300°C.:

(1) less than five parts by weight of a polyorganosiloxane having a viscosity of 200 to several million cs at 25°C. expressed by the general formula R²_b(R³O)_cSiO_{(4-b-c)/2} in which R² is a monovalent hydrocarbon or halogenated hydrocarbon group having 1 to 10 carbon atoms, R³ is hydrogen or a monovalent hydrocarbon group having 1 to 10 carbon atoms, b has an average value of from 1.9 to 2.2 and c has a sufficiently large value to give at least one -OR³ group in each molecule, said -OR³ group being present at least at the end of a molecular chain;
(2) 0.5 to 20 parts by weight for every 100 parts by weight of component (1) of one or more compounds selected from the following a) to d):

a) an organosilicon compound of the general formula R⁴_dSiX_{4-d} in which R⁴ is a monovalent hydrocarbon group having 1 to 5 carbon atoms, x is a hydrolyzable group and d has an average value of one or less;

b) a partially hydrolyzed condensate of said compound a);

c) a siloxane resin consisting essentially of (CH₃)₃SiO_{1/2} and SiO₂ units and having a (CH₃)₃SiO_{1/2}/SiO₂ ratio of 0.4/1 to 1.2/1; and
d) a condensate of said compound c) with said compound a) or b);

(3) 0.5 to 30 parts by weight of a finely divided filler for every 100 parts by weight of component (1);

(4) a catalytic amount of a compound for promoting the reaction of the other components; and

the secondary antifoam agent being a polydimethylsiloxane fluid, at least one nonionic

silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent and a second dispersing

5

agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent.

10

15

20

25

30

35

40

45


50

55

60

65

9



(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets

(11) Publication number:

0 354 016 A3

(12)

EUROPEAN PATENT APPLICATION(21) Application number: **89307851.9**(51) Int. Cl.⁵: **C11D 3/00, C11D 3/37**(22) Date of filing: **02.08.89**(30) Priority: **04.08.88 US 228079**(43) Date of publication of application:
07.02.90 Bulletin 90/06(84) Designated Contracting States:
BE DE ES FR GB NL(89) Date of deferred publication of the search report:
27.02.91 Bulletin 91/09(71) Applicant: **DOW CORNING CORPORATION**
3901 S. Saginaw Road
Midland Michigan 48686-0994(US)(72) Inventor: **Starch, Michael Stephen**
2644 N. 5 Mile Road
Midland Michigan(US)(74) Representative: **Lewin, John Harvey et al**
ELKINGTON AND FIFE Beacon House 113
Kingsway
London WC2B 6PP(GB)(54) **Dispersible silicone antifoam formulations.**

(57) A dispersible silicone antifoam composition for providing controlled foaming liquid laundry detergent formulations and wherein there is provided a non-aqueous emulsion of primary and secondary silicone antifoam agents, at least one nonionic silicone surfactant for emulsifying the primary and secondary antifoam agents in a solvent, a first organic surfactant dispersing agent for assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent and a second dispersing agent of a nonionic difunctional block-copolymer terminating in primary hydroxyl groups for further assisting in dispersing the emulsified primary and secondary antifoam agents in the liquid laundry detergent.

EP 0 354 016 A3



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 89 30 7851

| DOCUMENTS CONSIDERED TO BE RELEVANT | | | | | |
|--|---|--|---|---|---|
| Category | Citation of document with indication, where appropriate, of relevant passages | Relevant to claim | CLASSIFICATION OF THE APPLICATION (Int. Cl.5) | | |
| Y | EP-A-0 163 541 (DOW CORNING KABUSHIKI KAISHA) * the whole document *; & US-A-4639489 (cat. D); & US-A-4749740 (cat. D) - - - | 1-7 | C 11 D 3/00 C 11 D 3/37 | | |
| Y | EP-A-0 142 910 (THE PROCTER & GAMBLE LTD.) * the whole document * - - - | 1-7 | | | |
| A | FR-A-2 328 040 (THE PROCTER & GAMBLE CO.) * claims * - - - | 1,2 | | | |
| A | GB-A-2 119 394 (DOW CORNING CORPORATION) * the whole document * - - - | 1,2 | | | |
| A | EP-A-0 091 802 (THE PROCTER & GAMBLE) * the whole document * - - - - - | 1,2 | | | |
| The present search report has been drawn up for all claims | | | TECHNICAL FIELDS SEARCHED (Int. Cl.5) C 11 D 3/00 C 11 D 11/00 B 01 D 19/00 | | |
| Place of search Berlin | | Date of completion of search 22 November 90 | Examiner PELLI-WABLAT B | | |
| <table><tr><td>CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention</td><td>E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document</td></tr></table> | | | | CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention | E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document |
| CATEGORY OF CITED DOCUMENTS X: particularly relevant if taken alone Y: particularly relevant if combined with another document of the same category A: technological background O: non-written disclosure P: intermediate document T: theory or principle underlying the invention | E: earlier patent document, but published on, or after the filing date D: document cited in the application L: document cited for other reasons &: member of the same patent family, corresponding document | | | | |